

Avery Dennison[®] MPI 2002

Gloss White Transit Calendered Vinyl Removable

Features

- Excellent printability and handling on all latex, eco-solvent and solvent inkjet printers
- Specifically designed for transit wrap applications
- Dimensionally stable StaFlat liner provides easy converting properties
- Soft film provides easy application to curved surfaces
- Good outdoor durability and performance
- High gloss finish for superior appearance
- Grey adhesive provide excellent blockout performance
- Easy and clean removability with heat for up to 2 years

Conversion⁺

- | | |
|---|---|
| <input type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Electrostatic printing |
| <input type="checkbox"/> Die cutting | <input checked="" type="checkbox"/> Latex inkjet |
| <input type="checkbox"/> Thermal transfer | <input checked="" type="checkbox"/> Eco solvent inkjet |
| <input type="checkbox"/> Screen printing | <input checked="" type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Offset printing | <input checked="" type="checkbox"/> UV curable inkjet |

*Always test with your combination of printer and inks prior to commercial use.

Uses

Avery Dennison MPI 2002 is a gloss white polymeric vinyl film designed primarily for use in short term transit wrap applications where slight conformability, excellent opacity and removability are required.

Description



Film: 80 micron gloss white polymeric calendered vinyl



Adhesive: Grey removable acrylic
Removability: up to 2 years



Backing: Two side PE coated Staflat paper, 140g/m²



Outdoor life: Up to 7 years (unprinted)

Application surface: Flat, simple curves, gentle corrugations

Common Applications

- Trains and light rail
- Buses
- Outdoor advertising
- Flat sided trucks

Physical characteristics

General

| | | |
|--------------------------------|------------------------------|-------------------------|
| Calliper, face film | ISO 534 | 80 micron |
| Calliper, face film & adhesive | ISO 534 | 120 micron |
| Dimensional stability | DIN 30646 | 0.3 mm max |
| Adhesion, initial | FINAT FTM-1, stainless steel | 240 N/m |
| Adhesion, ultimate | FINAT FTM-1, stainless steel | 300 N/m |
| Removability ^^ | Smooth OEM painted surfaces | Up to 2 years |
| Flammability | | Self extinguishing |
| Shelf life | Stored at 22° C/50-55 % RH | 2 years |
| Durability ** | Vertical exposure ^ | Up to 7 years unprinted |

^ See ICS Performance Guarantee Durability Bulletin for your specific printer and ink combination for further information

^^ Not removable when applied to nitrocellulose paints, fresh screen print inks, ABS, polystyrene & certain types of PVC

Thermal

| | |
|-------------------------|------------------|
| Application temperature | Minimum: + 10°C |
| Temperature range | - 40°C to + 80°C |

Chemical

Resistant to most petroleum based oils, greases and aliphatic solvents

Resistant to most mild acids, alkalies, and salts

Note:

Materials have to be properly dried and cured before further processing, like laminating, varnishing, trimming, contour cutting or application. The residual solvents can otherwise change the products' specific features and properties.

Test Methods

Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the normal middle European and central North American regions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere; in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased. Please refer to Avery Dennison Instructional Bulletin 1.3 for definitions and reductions based on the 'Zone System'.

*Compatible with most media and ink combinations. Test prior to use.

***Information unavailable at time of printing.

Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.



Graphics
Solutions

Avery Dennison Graphics Solutions Asia Pacific

www.graphicsap.averydennison.com